






VINYL SPECIFICATIONS

TECHNICAL DATA	STANDARD	PRO SOMPLAN 350 <small>In stock</small>	PRO SOMPLAN 600 <small>on demand</small>	PRO FIELDS SPARK <small>on demand</small>	GREEN STORY	
Type of floor covering	EN ISO 10851 EN ISO 10852	Homogeneous		Heterogeneous	 	
Certification & classification						
Classification	EN ISO 10874	Commercial: 34 Industrial: 43		Commercial: 33 Heavy		
Technical characteristics						
Total thickness	EN ISO 24346	2mm			<p>Tarkett's commitment to the environment is woven throughout its business. Cradle-to-Cradle principles are, in fact, the basis of the design and production of every solution. Particularly, the lifecycle analysis is used to continuously improve the production process, and so the products until their use stage, disposal and recycling.</p> <p>Tarkett Human Conscious Design</p> <p>At Tarkett, we strive to support both our professional clients and consumers in creating healthy, beautiful and sustainable living spaces. Working with industry partners, we're bringing our best thinking and efforts towards making a positive impact on people and the planet. Since 2010, we have developed the use of a phthalate-free plasticizer technology for our vinyl floors which is approved for food containers and toys. Building a circular economy of programs and business models that encourage take-back, recycling, reuse and elimination of waste & inviting others to join us in Doing Good through education, collaborations, transparency and communication.</p>	
Wear layer thickness	EN ISO 24340	-		0.30mm / 0.55mm		
Total weight	EN ISO 23997	3150 g/m ²	2700 g/m ²	3200 g/m ²		
Dimensions - Width	EN ISO 24341 EN 426	2m				
Dimensions - Length	EN ISO 24341 EN 426	23 lm		20 lm		
Surface treatment	-	TEKTANIUM™ SURFACE PROTECT		PUR		
Technical performances						
Binder content	EN ISO 10581	Type II	Type I	Type I		
Dimensional stability	EN ISO 23999	≤ 0.40%				
Curl resultant to heat	EN ISO 23999	≤ 4.0mm		≤ 8.0mm		
Reaction to fire	EN 13501-1	B _s -s1 (Highest rating)				
Residual indentation	EN ISO 24343-1	≤ 0.10 mm		≤ 0.20 mm		
Castor chair test	ISO 4918 - EN 425	No damage				
Thermal resistance	EN ISO 10456	Approx. 0.01 (m ² .K)/W				
Light fastness	EN ISO 105-B02	≥ 6				
Chemical resistance	EN ISO 26987	Good resistance				
Slip resistance	DIN 51130	R9				
Static electrical charge	EN 1815	≤ 2kV				
Bacteria resistance	ISO 846-C	Doesn't favour growth		-		
Flexibility	ISO 24344	20mm		No crack		
Clean room	ISO 14644-1	ISO Class 3	ISO Class 2	-		
Environment						
TVOC emission 28 days	ISO 16000	≤ 10µg/m ³		≤ 100µg/m ³		
Recyclable	-	100%				
Plasticizer	-	Phthalate-free				
SGBC	-	SGBC Certified - Excellent		A/f		
Warranty	-	15 years commercial		10 years commercial		

The above information is subject to modification for the benefits of further improvement.

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

The designs and photos used in this brochure are for illustration purposes only. They are not contractual images and do not stand for product or installation recommendation.



Distributed By

